







DELTA RIB™ III




Delta Rib III

Delta Rib III panel is a light gauge, exposed fastener panel with 36" coverage used in both roof and wall applications.

FEATURES AND BENEFITS

- Available in our Dura Tech™ xl paint system or our ZINCALUME® Plus finish for unpainted applications; limited lifetime warranty available on residential applications.
- ColorGuard 25 with Spectrascape[®] available with a 25 year limited warranty for your agricultural, post frame and recreational building applications.
- Specialty prints in Dura Tech xl paint system available in 29ga as a standard offer.
- Matching polycarbonate panels available.
- Manufactured with high tensile steel for greater load capability.
- Economical standard and custom trim packages available with every order.
- Product is UL Class A Fire Rated when installed in accordance with UL requirements.
- Building Code Approval Report: #ER-0550

STANDING BY OUR PRODUCTS AND WARRANTIES FOR 40 YEARS











DELTA RIB™ III



COOL Dura Tech xl keeps the heat out and the color brilliant.


- Superior color retention and resistance to chalk and fade.
- Dura Tech xl energy saving COOL colors reduce the demand for energy.





A robust and economical paint system.

- · Resistant to chalk and fade with ratings similar to a PVDF.
- · Engineered to resist peeling or cracking for 25 years.











Product Availability by Gauge and Location

| Location | Salem, Oregon | | | | |
|---------------|---------------|--|--|--|--|
| Dura Tech xI | 29ga & 26ga | | | | |
| ColorGuard 25 | 29ga | | | | |

Additional lead times apply on products supplied from a non-local facility.

Not all facilities produce product in premium colors. Please allow additional lead time for shipment to other service areas.

REPRESENTATION OF COLORS MAY VARY DUE TO **PRINTING LIMITATIONS.**

Sample color chips are available upon request. Consult your ASC Building Products representative for more information.

29

26

Г

0.0139

0.0173

80

80

Natural Rust7

26 Gauge (Subject to upcharge)

LOAD TABLE

| | | | Positive (Inward) Uniform Load Capacity (lbs/ft²) / Span (ftin.) | | | | | | | | |
|-------|----------------|----------|--|-------|-------|-------|-------|-------|-------|-------|-------|
| Gauge | Span | Cond. | 16" | 2'-0" | 2′-6" | 3'-0" | 3'-6" | 4'-0" | 4'-6" | 5'-0" | 6'-0" |
| | Single Span | ASD, W/Ω | 242 | 107 | 68 | 48 | 35 | 27 | 21 | 17 | 12 |
| | | L/180 | - | - | - | 40 | 25 | 17 | 12 | 9 | 5 |
| 29 | Double Span | ASD, W/Ω | 238 | 110 | 71 | 49 | 36 | 28 | 22 | 17 | 12 |
| 29 | | L/180 | - | - | - | - | - | - | - | - | - |
| | Triple Span | ASD, W/Ω | 289 | 135 | 88 | 62 | 45 | 35 | 27 | 23 | 15 |
| | | L/180 | - | - | - | - | - | 32 | 23 | 16 | 10 |
| | Single Span | ASD, W/Ω | 332 | 147 | 94 | 65 | 48 | 37 | 29 | 24 | 16 |
| | | L/180 | - | - | 88 | 51 | 32 | 21 | 15 | 11 | 6 |
| 26 | Double Span | ASD, W/Ω | 310 | 141 | 90 | 63 | 46 | 36 | 28 | 23 | 16 |
| 20 | | L/180 | - | - | - | - | - | - | - | - | 15 |
| | Triple Span | ASD, W/Ω | 379 | 174 | 112 | 78 | 58 | 45 | 35 | 28 | 20 |
| | | L/180 | - | - | - | - | - | 40 | 28 | 21 | 12 |

Copper Penny[†]

29 Gauge

NOTES

Top values based on allowable stress (ASD). Bottom values based on a deflection limit of L/180.

"-" denotes that the allowable load is limited by the panel stress vs. deflection limit

Steel conforms to ASTM A653 (Galvanized) or ASTM A792 (ZINCALUME) structural steel. Tabulated values are for positive (inward) uniform loading only.

Values are based on the American Iron and Steel Institute "Cold Formed Steel Design Manual" (AISI S100-12). Refer to ascbp.com for more complete Delta Rib III performance data

| Properties | | | | | | | | | | | |
|------------|---------------------------------|----------------|------------------|------------------|----------------|----------------|----------------|----------------|--|--|--|
| Gauge | Base Steel Thickness (in) | Yield (ksi) | Tensile (ksi) | Wt. (lbs/ft²) | l+ (in⁴/ft) | S+ (in³/ft) | l- (in⁴/ft) | S- (in³/ft) | | | |

0.65

0.80

0.0124

0.0179

0.0157 | 0.0245

0.0104

0.0134


0.0191

0.0242

NOTES: The moments of inertia, I+ and I-, presented for determining deflection are: (2I_{Effe}

82

82



ASC Building Products is Proudly Distributed by:

[†] Please note these colors are batch sensitive (may have color variation) and are directional in nature. Different batches are not to be mixed on projects. We recommend that you request a sample of current stocked material to review actual color before ordering to ensure color accuracy. We are not responsible for color variations.